U.S. DEPARTMENT OF ENERGY | Energy Efficiency & Renewable Energy

Bandwidth Study on Energy Use and Potential Energy Saving Opportunities in the Manufacturing of Lightweight Materials: Advanced High Strength Steel

March 15, 2016

Prepared for: National Renewable Energy Laboratory and U.S. Department of Energy, Advanced Manufacturing Office

Prepared by: Energetics Incorporated

DRAFT REPORT

DRAFT

(This page intentionally left blank)

DRAFT

Preface

Reducing energy consumption through investment in advanced technologies and practices can enhance American manufacturing competitiveness. Energy bandwidth studies of U.S. manufacturing sectors serve as general data references to help understand the range (or *bandwidth*) of potential energy savings opportunities. [1] The U.S. Department of Energy (DOE)'s Advanced Manufacturing Office (AMO) has commissioned a series of bandwidth studies to analyze the manufacturing of products that can be used for lightweighting applications, and provide hypothetical, technology-based estimates of potential energy savings opportunities in the manufacturing process. The consistent methodology used in the bandwidth studies provides a framework to evaluate and compare energy savings potentials within and across manufacturing sectors at the macro-scale.

AMO is releasing this energy bandwidth study in draft form in order to solicit input from the public as part of the peer review process. This study is being released as part of a series of six studies focusing on energy use in the manufacture of the following lightweight structural materials: carbon fiber reinforced polymer composites, glass fiber reinforced polymer composites, advanced high-strength steel, aluminum, magnesium, and titanium. Reviewer feedback will be used to update the bandwidth reports with the best available data and assumptions prior to final publication, and to generate input to support further analysis. In the next phase of work, data will be integrated and compared across all six materials, including a comparison of manufacturing energy intensity on a material performance (e.g., effective weight) basis for key applications.



Energy Consumption Bands and Opportunity Bandwidths Estimated in this Study

Four different energy *bands* (or measures) are used consistently in this series to describe different levels of onsite energy consumption to manufacture specific products and to compare

[1] The concept of an energy bandwidth, and its use as an analysis tool for identifying potential energy saving opportunities, originated in AMO in 2002 (when it was called the Office of Industrial Technologies). Most recently, revised and consistent versions of bandwidth studies for the *Chemicals, Petroleum Refining, Iron and Steel*, and *Pulp and Paper* sectors were published in 2015.

DRAFT

potential energy savings opportunities in U.S. manufacturing facilities (see figure). **Current typical** (CT) is the energy consumption in 2010; **state of the art** (SOA) is the energy consumption that may be possible through the adoption of existing best technologies and practices available worldwide; **practical minimum** (PM) is the energy consumption that may be possible if applied R&D technologies under development worldwide are deployed; and the **thermodynamic minimum** (TM) is the least amount of energy required under ideal conditions, which typically cannot be attained in commercial applications. CT energy consumption serves as the benchmark of manufacturing energy consumption. TM energy consumption serves as the baseline (or theoretical minimum) that is used in calculating energy savings potential. Feedstock energy (the nonfuel use of fossil energy) is not included within the energy consumption estimates.

Two onsite energy savings opportunity *bandwidths* are estimated: the ***current opportunity*** spans the bandwidth from CT energy consumption to SOA energy consumption, and the ***R&D opportunity*** spans the bandwidth from SOA energy consumption to PM energy consumption. The difference between PM energy consumption and TM energy consumption is labeled as *impractical*. The term *impractical* is used because with today's knowledge of technologies in R&D, further investment may no longer lead to incremental energy savings and thermodynamic limitations impede technology opportunities. Significant investment in technology development and implementation would be needed to fully realize the energy savings opportunities estimated. The costs associated with achieving SOA and PM energy consumption are not considered in this report; a techno-economic analysis of the costs and benefits of future R&D technologies was not in the scope of this study.

For each lightweighting material studied in the series, the four energy bands are estimated for select individual subareas of the material manufacturing process. The estimation method involved a detailed review and analytical synthesis of data from diverse industry, governmental, and academic sources. Where published data were unavailable, best engineering judgment was used.

DRAFT

Acknowledgments

Joseph Cresko of DOE/AMO led the conceptual development and publication of the bandwidth study series with support from Dr. Alberta Carpenter of the National Renewable Energy Laboratory. AMO recognizes the efforts of Subodh Das, Caroline Kramer, Dr. Aaron Fisher, and Sabine Brueske of Energetics Incorporated for conducting the research and analysis and writing this study.

Executive Summary

The United States is a significant producer of iron and steel products, especially specialty grades such as advanced high strength steel (AHSS). This bandwidth study examines energy consumption and potential energy savings opportunities in U.S. AHSS manufacturing for lightweighting applications. Industrial, government, and academic data are used to estimate the energy consumed in six of the most energy intensive manufacturing subareas. Three different energy consumption *bands* (or levels) are estimated for these select manufacturing subareas based on referenced energy intensities of current, state of the art, and R&D technologies. A fourth theoretical minimum energy consumption *band* is also estimated. The *bandwidth*—the difference between bands of energy consumption—is used to determine the potential energy savings opportunity. The costs associated with realizing these energy savings was not in the scope of this study.

The purpose of this data analysis is to provide macro-scale estimates of energy savings opportunities for each AHSS manufacturing subarea. This is a step toward understanding the processes that could most benefit from technology and efficiency improvements to realize energy savings.

Study Organization and Approach: After providing an overview of the methodology and boundaries (Chapter 1) the 2010 production volumes (Chapter 2) and current energy consumption (current typical [CT], Chapter 3) were estimated for six select subareas. In addition, the minimum energy consumption for these processes was estimated assuming the adoption of best technologies and practices available worldwide (state of the art [SOA], Chapter 4) and assuming the deployment of the applied research and development (R&D) technologies available worldwide (practical minimum [PM], Chapter 5). The minimum amount of energy theoretically required for these processes assuming ideal conditions was also estimated (thermodynamic minimum [TM)], Chapter 6); in some cases, this is less than zero. The difference between the energy consumption *bands* (CT, SOA, PM, TM) are the estimated energy savings opportunity *bandwidths* (Chapter 7).

In this study, CT, SOA, PM, and TM energy consumption for six *individual* subareas is estimated from multiple referenced sources.

Study Results: Two energy savings opportunity *bandwidths* – current opportunity and R&D opportunity – are presented in Table ES-1 and Figure ES-1.[2] The current opportunity is the difference between the 2010 CT energy consumption and SOA energy consumption; the R&D opportunity is the difference between SOA energy consumption and PM energy consumption.

[2] The energy estimates presented in this study are for macro-scale consideration; energy intensities and energy consumption values do not represent energy use in any specific facility or any particular region in the United States. The costs associated with achieving energy savings are not considered in this study. All estimates are for onsite energy use (i.e., energy consumed within the plant boundary). Energy used as feedstocks (non-fuel inputs) to production is excluded.

DRAFT

Potential energy savings opportunities are presented for the U.S. advanced high strength steel manufacturing subareas studied and as a total.

The U.S. iron and steel industry operated at relatively low capacity utilization and lower-than-typical efficiencies in 2010, due in large part to the economic downturn. While the specific impacts of the economic factors in 2010 are not directly identified in this report, it is reasonable to assume that the current opportunity is likely somewhat exaggerated, as a portion of the current savings could be achieved by simply optimizing production rates. For this reason the border between current opportunity and R&D opportunity is not explicitly defined, and a dashed line and color fading is used in Figure ES-1. Also, AHSS production has seen growth in the past several years, especially with increased application in the automotive sector. Therefore, it is important to note that the total energy opportunities would scale with increasing production.

Table ES-1. Potential Energy Savings Opportunities in the U.S. Advanced High Strength Steel Manufacturing Sector (Considering Production for Lightweighting Application Areas only)*

Opportunity Bandwidths	Estimated Energy Savings Opportunity for Select Advanced High Strength Steel Manufacturing Subareas (per year)
Current Opportunity **– energy savings if the best technologies and practices available are used to upgrade production.** [3, 4]	**7 TBtu** (55% energy savings, where TM is the baseline)
R&D Opportunity **– additional energy savings if the applied R&D technologies under development worldwide are deployed.** [5, 6]	**2 TBtu** (16% energy savings, where TM is the baseline)

* Calculated using the production values for lightweight structural application areas considered in this study only (see Section 1.4), and not all AHSS.

[3] Current opportunity savings calculation: 7 TBtu = 18 – 11 TBtu
[4] Current opportunity energy savings percentage = [(CT – SOA)/(CT – TM)] x 100
[5] R&D opportunity savings calculation: 2 TBtu = 11 – 8 TBtu
[6] R&D opportunity energy savings percentage = [(SOA – PM)/(CT – TM)] x 100

DRAFT



Figure ES-1. Current and R&D Energy Savings Opportunities for the Advanced High Strength Steel Manufacturing Subareas Studied (Considering Lightweighting Application Area Production Only)

DRAFT

The PM energy consumption estimates are speculative because they are based on unproven technologies. The estimates assume the successful deployment of R&D technologies that are under development; where multiple technologies were considered for a similar application, only the most energy efficient technology was considered in the energy savings estimate. The difference between PM and TM is labeled "impractical" in Figure ES-1 because with today's knowledge of technologies in R&D, further investment may no longer lead to incremental energy savings and thermodynamic limitations impede technology opportunities.

An estimated 17.62 TBtu of energy was consumed in 2010 to manufacture AHSS in the U.S. for the structural applications considered in this study. Based on the results of this study, an

estimated 6.7 TBtu of energy could be saved each year if capital investments in the best technologies and practices available worldwide were used to upgrade the advanced high strength steel manufacturing subareas studied; an additional 2.0 TBtu could be saved through the adoption of applied R&D technologies under development worldwide.

The top three current energy savings opportunities for AHSS are as follows:

- Cold rolling – 3.3 TBtu (or 49% of the current opportunity)
- Hot rolling – 2.2 TBtu (or 33% of the current opportunity)
- Basic oxygen furnace steelmaking – 0.5 TBtu (or 7% of the current opportunity).

The top three R&D energy savings opportunities for AHSS are as follows:

- Blast furnace ironmaking – 1.0 TBtu (or 50% of the R&D opportunity)
- Cold rolling – 0.4 TBtu (or 18% of the R&D opportunity)
- Hot rolling – 0.3 TBtu (or 14% of the R&D opportunity).

DRAFT

List of Acronyms and Abbreviations

AHSS	Advanced High Strength Steel
AISI	American Iron and Steel Institute
AMO	Advanced Manufacturing Office
AOD	Argon oxygen decarburization
BF	Blast furnace
BFG	Blast furnace gas
BOF	Basic oxygen furnace
Btu	British thermal unit
COE	Cost of energy
COG	Coke oven gas
CT	Current typical energy consumption or energy intensity
DOE	U.S. Department of Energy
DRI	Direct-reduced iron
EAF	Electric arc furnace
EERE	DOE Office of Energy Efficiency and Renewable Energy
EIA	U.S. Energy Information Administration
EPA	U.S. Environmental Protection Agency
GJ	Gigajoules
HHV	Higher heating value
IEA	International Energy Agency
K	Kelvin
kWh	Kilowatt hours
LHV	Lower heating value
MECS	Manufacturing Energy Consumption Survey
mm	Millimeter
MMBtu	Million British thermal units
MT	Metric ton (tonne)
NAICS	North American Industry Classification System
PJ	Petajoules
PM	Practical minimum energy consumption or energy intensity
SOA	State of the art energy consumption or energy intensity
TBtu	Trillion British thermal units
TM	Thermodynamic minimum energy consumption or energy intensity

DRAFT

Table of Contents

Preface ii
Acknowledgments iii
Executive Summary iv
List of Acronyms and Abbreviations viii
Table of Contents ix
List of Tables x
List of Figures x
1. Introduction 1
1.1. Overview 1
1.2. Definitions of Energy Consumption Bands and Opportunity Bandwidths 1
1.3. Bandwidth Analysis Method 2
1.4. Boundaries of the AHSS Bandwidth Study 4
2. Advanced High Strength Steel Production 6
2.1. Manufacturing Overview 6
2.2. Production Values 9
3. Current Typical Energy Intensity and Energy Consumption 11
3.1. Sources for Current Typical Energy Intensity 11
3.2. Current Typical Energy Intensity and Energy Consumption 12
4. State of the Art Energy Intensity and Energy Consumption 14
4.1. Sources for State of the Art Energy Intensity 14
4.2. State of the Art Energy Intensity and Energy Consumption 15
5. Practical Minimum Energy Intensity and Energy Consumption 18
5.1. Sources for Practical Minimum Energy Intensity 18
5.2. Practical Minimum Energy Intensity and Energy Consumption 19
6. Thermodynamic Minimum Energy Intensity and Energy Consumption 22
6.1. Sources for Thermodynamic Minimum Energy Intensity 22
6.2. Thermodynamic Minimum Energy Intensity and Energy Consumption 23
7. Current and R&D Opportunity Analysis/Bandwith Summary 25
8. References 28
Appendix A1. Master AHSS Summary Table 36
Appendix A2: References for Production, CT, SOA, PM, TM 37
Appendix A3: Practical Minimum Energy Intensity Calculation and Technologies Considered 38

DRAFT

List of Tables

Table ES-1. Potential Energy Savings Opportunities in the U.S. Advanced High Strength Steel Manufacturing Sector (Considering Production for Lightweighting Application Areas only)* v
Table 2-1. Advanced High Strength Steel Manufacturing Process Areas Considered in Bandwidth Analysis 8
Table 2-2. U.S. Advanced High Strength Steel Subarea Products and Production in 2010 9
Table 3-1. Main Sources Referenced in Identifying Current Typical Intensity by Subarea and Material Total 12
Table 3-2. Onsite CT Energy Intensity and Calculated Energy Consumption and Calculated Primary CT Energy Consumption for U.S. AHSS Manufacturing – Application Areas Studied (2010) 13
Table 4-1. Main Sources Referenced in Identifying State of the Art Intensity by Process Area and Material Total 15
Table 4-2. SOA Energy Intensities and Calculated SOA Energy Consumption for AHSS Manufacturing – Application Areas Considered 16
Table 4-3. Calculated SOA Energy Consumption for AHSS Manufacturing – Application Areas Studied 17
Table 5-1. Sources Referenced in Identifying Practical Minimum Intensity by Process Area and Material Total 18
Table 5-2. Calculated PM Energy Consumption for AHSS Manufacturing – Application Areas Considered 19
Table 5-3. Calculated PM Energy Consumption for AHSS Manufacturing – Application Areas Studied 20
Table 6-1. Calculated TM Energy Consumption for AHSS Manufacturing – Application Areas Considered 24
Table 7-1. Current and R&D Opportunity for AHSS Manufacturing – Application Areas Studied 26

List of Figures

Figure ES-1. Current and R&D Energy Savings Opportunities for the Advanced High Strength Steel Manufacturing Subareas Studied (Considering Lightweighting Application Area Production Only) vi
Figure 1-1. Estimated Makeup of the AHSS Market in 2010 5
Figure 2-1. Steelmaking Flowlines for Integrated (Top) and Mini Mills (Bottom) (AISI 2013b) . 8
Figure 7-1. Current and R&D Energy Savings Opportunities in U.S. AHSS Manufacturing for the Subareas and Application Areas Studied 27

DRAFT

1. Introduction

1.1. Overview

The U.S. Department of Energy (DOE)'s Advanced Manufacturing Office (AMO) has commissioned a series of bandwidth studies to analyze processes and products that are highly energy intensive, and provide hypothetical, technology-based estimates of energy savings opportunities. Reducing energy consumption through investment in advanced technologies and practices can enhance American manufacturing competitiveness. Manufacturing energy bandwidth studies serve as general data references to help understand the range (or *bandwidth*) of energy savings opportunities. DOE AMO commissioned this bandwidth study to analyze the most energy consuming processes in manufacturing advanced high strength steel (AHSS).

This study is one in a series of six bandwidth studies characterizing energy use in manufacturing lightweight structural materials in the U.S. The other materials, studied in parallel, include: aluminum, magnesium, titanium, carbon fiber reinforced composites, and glass fiber reinforced composites. Separate studies are available for these materials. As a follow-up to this work, an integrating analysis will be conducted to compare the results across all six studies.

Similar energy bandwidth studies have also been prepared for four U.S. manufacturing sectors – chemicals (DOE 2015a), iron and steel (DOE 2015b), petroleum refining (DOE 2015c), and pulp and paper (DOE 2015d). These studies follow the same analysis methodology and presentation format as the seven lightweight structural material energy bandwidth studies.

1.2. Definitions of Energy Consumption Bands and Opportunity Bandwidths

The consistent methodology used in the bandwidth studies provides a framework to evaluate and compare energy savings potentials within and across manufacturing sectors at the macro-scale.

Four different energy *bands* (or measures) are used consistently in this series to describe different levels of onsite energy consumption to manufacture specific products and to compare energy savings opportunities in U.S. manufacturing facilities. **Current typical** (CT) is the energy consumption in 2010; **state of the art** (SOA) is the energy consumption that may be possible through the adoption of existing best technologies and practices available worldwide; **practical minimum** (PM) is the energy consumption that may be possible if applied R&D technologies under development worldwide are deployed; and the **thermodynamic minimum** (TM) is the least amount of energy required under ideal conditions, which typically cannot be attained in commercial applications.

DRAFT

CT energy consumption serves as the benchmark of manufacturing energy consumption. TM energy consumption serves as the baseline (or theoretical minimum) that is used in calculating energy savings potential. Feedstock energy (the nonfuel use of fossil energy) is not included in the energy consumption estimates.

Two onsite energy savings opportunity *bandwidths* are estimated: the ***current opportunity*** spans the bandwidth from CT energy consumption to SOA energy consumption, and the ***R&D opportunity*** spans the bandwidth from SOA energy consumption to PM energy consumption. The difference between PM energy consumption and TM energy consumption is labeled as *impractical*. The term *impractical* is used because with today's knowledge of technologies in R&D, further investment may no longer lead to incremental energy savings and thermodynamic limitations impede technology opportunities. Significant investment in technology development and implementation would be needed to fully realize the energy savings opportunities estimated. The costs associated with achieving SOA and PM energy consumption are not considered in this report; a techno-economic analysis of the costs and benefits of future technologies was not in the scope of this study.



Energy Consumption Bands and Opportunity Bandwidths Estimated in this Study

1.3. Bandwidth Analysis Method

This Section describes the method used in this bandwidth study to estimate the four bands of energy consumption and the two corresponding energy savings opportunity bandwidths. This section can also be used as a guide to understanding the structure and content of this report.

In this study, U.S. energy consumption is labeled as either "onsite energy" or "primary energy" and defined as follows:

- **Onsite energy** (sometimes referred to as site or end use energy) is the energy consumed within the manufacturing plant boundary (i.e., within the plant gates). Non-fuel feedstock energy is *not* included in the onsite energy consumption values presented in this study.
- **Primary energy** (sometimes referred to as source energy) includes energy that is consumed both offsite and onsite during the manufacturing process. Offsite energy consumption includes generation and transmission losses associated with bringing

DRAFT

electricity and steam to the plant boundary. Non-fuel feedstock energy is not included in the primary energy values. Primary energy is frequently referenced by governmental organizations when comparing energy consumption across sectors.

The four bands of energy consumption described above are quantified for process subareas and for the material total. **The bands of energy consumption and the opportunity bandwidths presented herein consider onsite energy consumption; feedstocks[7] are excluded.** To determine the total annual onsite CT, SOA, PM, and TM energy consumption (TBtu per year), energy intensity values per unit weight (Btu per pound of material manufactured) were estimated and multiplied by the production (pounds per year of material manufactured). The year 2010 was used as a base year since it is the most recent year for which consistent energy consumption and production data were available for all six lightweight materials analyzed in this series of bandwidth studies. Unless otherwise noted, 2010 production data were used. Some production processes are exothermic and are net producers of energy; the net energy was considered in the analysis.

Chapter 2 presents the **U.S. production** (million pounds per year) in 2010, including an overview of major application areas. Four structural application areas are included with the scope of this bandwidth report. The production volumes for these application areas were estimated from market data.

Chapter 3 presents the calculated onsite **CT energy intensity** (Btu per pound) and **CT energy consumption** (TBtu per year) for the process subareas studied and material total (along with sources).

Chapter 4 presents the estimated onsite **SOA energy intensity** (Btu per pound) and **SOA energy consumption** (TBtu per year) for the process subareas studied and material total (along with sources).

Chapter 5 presents the estimated onsite **PM energy intensity** (Btu per pound) and **PM energy consumption** for the process subareas studied and material total (along with sources).

Chapter 6 presents the estimated onsite **TM energy intensity** (Btu per pound) and **TM energy consumption** for the process subareas studied and material total (along with sources).

Chapter 7 provides a summary of **current and R&D opportunity** analysis based on bandwidth study results.

[7] Feedstock energy is the nonfuel use of combustible energy. Feedstocks are converted to iron and steel products (not used as a fuel); MECS values reported as "feedstocks" exclude feedstocks converted to other energy products.

DRAFT

1.4. Boundaries of the AHSS Bandwidth Study

The U.S. manufacturing sector is the physical boundary of study. It is recognized that the major benefits of lightweight materials often occur *outside* of the manufacturing sector—for example, the energy benefits of a lightweight automobile component are typically realized primarily through fuel savings during the vehicle's use phase. Economic impacts may also be important: an advanced lightweight aerospace component may be more expensive than the conventional choice. While such impacts are recognized as important, they will not be quantified as this is not a life cycle assessment study. Instead, this report focuses exclusively on the energy use directly involved in the production of AHSS from the relevant input materials. The focus of this bandwidth study is thus the *onsite* use of process energy (including purchased energy and onsite generated steam and electricity) that is directly applied to AHSS manufacturing at a production facility.

This study does not consider life cycle energy consumed during raw material extraction, off-site treatment, transportation of materials, product use, or disposal. For consistency with previous bandwidth studies, feedstock energy and the energy associated with delivering feedstocks to the plant gate (e.g., producing, conditioning, and transporting feedstocks) are *excluded* from the energy consumption bands in this analysis.

Steel is used in many diverse applications that differ substantially in product use, performance requirements, and relevance to energy use. AHSS is widely used in transportation applications, where mass reductions can provide substantial energy savings through improved fuel economy. These applications are of high relevance to the DOE because of the potential life cycle energy savings. Other applications, such as in medical, electronics and communications, computers and electrical equipment, construction and infrastructure, and consumer goods and packaging, may be less relevant to DOE. In order to focus exclusively on structural applications with strong relevance to energy use, this study was limited to four key application areas:

1) Automotive lightweighting (e.g., vehicle chassis, body, doors);
2) Compressed gas storage (e.g., hydrogen fuel tanks for electric vehicles);
3) Wind turbines (e.g., lighter and longer turbine blades); and
4) Aerospace (e.g., aircraft fairings, fuselages, floor panels).

The first three of these application areas are consistent with the areas of interest outlined in the DOE *Composite Materials and Structures* Funding Opportunity Announcement (DOE 2014). The last application area (aerospace) is an additional high value-add market for lightweight structural materials. Based on the production numbers available, it was assumed that approximately 100% of overall AHSS production in the U.S. is for use in automotive lightweighting, as shown in Figure 1-1 (see Section 2.2 for more detail).

DRAFT



Figure 1-1. Estimated Makeup of the AHSS Market in 2010.

DRAFT

2. Advanced High Strength Steel Production

Steel is a vital domestic manufacturing product and is important for many applications including construction (residential, commercial, transportation), automotive, machinery and equipment, containers, and national security, among others. Steel is widely used in vehicles, making up over half of the composition of vehicles today (WSA 2014). Advanced high strength steel (AHSS), while also used in vehicles today, offers weight reduction possibilities of 25-39% compared to conventional steel, helping to reduce the lifecycle energy use and emissions of vehicles even further (WSA 2014). This is why steelmakers are interested in producing higher quantities and new grades of AHSS for the growing vehicle market.

2.1. Manufacturing Overview

Iron and steel operations are complex and large facilities that produce significant quantities of steel each year. Steel mills in the U.S. are generally either integrated mills, or mini mills; the primary difference being the proportion of recycled steel that is used (up to 99% in mini mills and was 91% in 2010 for all steel (USGS 2012c)). This proportion must be lower for grades of AHSS, which require less contaminants in order to gain the resulting desired properties. There is little information on the properties of steel recycled in 2010, making it difficult to determine what amounts and types of tramp elements and alloying elements are present during the BOF and EAF steelmaking processes. Additionally, elements may be considered as tramp elements in one case or an alloying element in another case, depending upon the grade of steel being produced (Worrell & Reuter 2014). There is no commercial refining process for tramp elements available today, and it is also possible for these elements to enter the system through ore or reductants used (in addition to the steel scrap) (Worrell & Reuter 2014). To compensate for the existence of tramp elements, producers of high quality grades of steel such as AHSS must depend on a source of well sourced scrap, obsolete scrap, or the use of ore-based iron units (such as direct reduced iron or hot briquetted iron) as input to the EAF in lieu of a portion of the scrap (Worrell & Reuter 2014).

The distribution of many of the integrated and mini mills in the United States is shown in Figure 2-1. Integrated steel mills produce steel from iron ore via the blast furnace (BF) and basic oxygen furnace (BOF) steelmaking technology while mini steels mills produce steel mostly from recycled scrap steel via the electric arc furnace (EAF) steelmaking technology. Figure 2-1 shows the steel industry process flowlines for integrated mills and for mini mills.

In 2010, there were about 15 BF/BOF steelmaking facilities operated by five companies and 112 EAF steelmaking facilities operated by over 50 companies in the U.S. (USGS 2012a). Most of these steelmaking facilities in the U.S. are concentrated in Indiana, Ohio, Pennsylvania, Michigan, and Illinois due to the close proximity to coal and iron ore suppliers, among other factors. In 2010, all iron and steel manufacturing directly employed 135,000 workers and total employment (including both direct and indirect employees in other industries) was estimated at

DRAFT

1,080,000 (AISI 2013a). It is unclear which of these facilities produce AHSS grades in addition to carbon, stainless, and other grades of steels, as well as the relative amounts.



Figure 2-1. Steelmaking Flowlines for Integrated (Top) and Mini Mills (Bottom) (AISI 2013b)

DRAFT

This study focuses on energy consumption in six energy intensive process areas in steel manufacturing. These process areas are identified in Table 2-1, along with some of the major sub-processes. Energy intensity and consumption is evaluated by subarea and sub-processes for CT, SOA, PM, and TM in Sections 3 through 6 of this report. Current energy intensity for pelletizing iron ore is shown for reference purpose only because this sub-process is outside the boundary of bandwidth analysis. Direct reduction ironmaking was not used in the United States in 2010, and therefore not included in the CT, SOA, PM, and TM bandwidth measures and savings summary.

Table 2-1. Advanced High Strength Steel Manufacturing Process Areas Considered in Bandwidth Analysis

Subareas	Sub-Processes
Agglomeration	Sintering
Cokemaking	
Ironmaking	Blast Furnace
Basic Oxygen Furnace (BOF) Steelmaking	
Electric Arc Furnace (EAF) Steelmaking	
Casting/Rolling	Continuous Casting Hot Rolling Cold Rolling

There are two main processes for producing steel: integrated steelmaking, which combines a blast furnace (BF) with a basic oxygen furnace (BOF), and electric arc furnace (EAF) steelmaking. These two processes are distinctly different as the integrated BOF process consumes mostly agglomerated iron ore along with some scrap steel (up to 30%; was 24% in 2010 for all steel (USGS 2012c)) while the EAF process consumes mostly scrap steel as well as reduced iron, cast iron, and other iron containing materials to produce raw steel (WCA 2013). Steel grades such as AHSS require specific compositions, meaning that there is less of a possibility of using an increased amount of recycled steel to produce AHSS.

It requires about seven times the amount of energy to produce a ton of steel from ore in a blast furnace and BOF (including the energy for cokemaking, pelletizing, and sintering), compared to remelting scrap in an electric arc furnace (not including losses for generating and transmitting electricity) (IPPC 2013; LBNL 2008). However, many other factors come in to play in the economics of ore-based versus scrap-based steelmaking. For agglomeration, pelletizing was not included in the production or energy intensity numbers because this process occurs outside of the boundary of this bandwidth analysis (pelletizing is usually conducted near the ore mining site, and not at the steel mill).

DRAFT

2.2. Production Values

Production data for total AHSS produced in the U.S. (or worldwide) is generally not available or collected as a whole. However, sector-side iron and steel manufacturing production data is available by process and sector-wide. The American Iron and Steel Institute (AISI) is the leading source for information on total steel production in North America. The AISI Statistical Summary is released annually and provides production data along with other statistical information. Total iron and steel sector production data for 2010 is summarized in Table 2-2. The AHSS estimated production column in Table 2-2 is calculated based on data available on AHSS production for the automotive sector in North America (sources AISI 2015, Demeri 2013, and March 2014). Based on figures provided by AISI 2015, it is assumed that all of the AHSS produced in 2010 for the North American automotive market is cold rolled.

Table 2-2. U.S. Advanced High Strength Steel Subarea Products and Production in 2010

Subarea	Product	2010 Total Steel Sector Production (million lb)	2010 AHSS Estimated Production (million lb)
Agglomeration			
Sintering*	Sinter	11,518	178
Cokemaking	Coke	18,584	287
Ironmaking**	Iron	59,180	914
BOF Steelmaking***	Raw Steel	68,690	1,061
EAF Steelmaking***	Raw Steel	108,772	1,681
Casting/Rolling			
Casting	Continuous Cast Steel	169,567	2,702
Hot Rolling	Hot Rolled Steel	169,567	2,702
Cold Rolling	Cold Rolled Steel	55,421	2,702

* Represents sinter consumption in steel mill blast furnaces; assumed to be produced domestically.
** Excludes limited production of ITmk3-produced iron nuggets.
*** Detailed data on which pathway was used to produce AHSS was unavailable for 2010; therefore, the split of 39% BOF route and 61% EAF route was assumed for this report. It is recognized that the amount of scrap vs. ore used as inputs to the steelmaking process may vary depending upon the specific facility but that information is general unavailable for citation. Modifications of this assumption would result in a different total energy consumption.
Data sources: AISI 2011a, AISI 2015, Demeri 2013, Marcus 2014.

While AHSS would have applicability for the four applications considered for this study (automotive lightweighting, compressed gas storage, wind turbines, and aerospace and other transportation), the automotive sector is the most notable application area and for which steel consumption data was available. It was therefore assumed that this application consumes a significant majority of AHSS produced in the U.S., which is small compared to the total amount of steel produced. However, the energy intensity numbers provided in this report are the basis for

DRAFT

the total energy consumption, and can be used to calculate the consumption for various steel grade production values, including AHSS.

Throughout the report, energy intensities are presented as Btu per lb of product for a specific subarea (e.g., for cokemaking the energy intensity is in Btu per lb of coke produced). This is how results are typically presented in the iron and steel industry and data available from sources was presented in this way.

DRAFT

3. Current Typical Energy Intensity and Energy Consumption

This chapter presents the energy consumption data for individual advanced high strength steel manufacturing subareas in 2010 for the boundary application areas production. Energy consumption in a manufacturing process can vary for diverse reasons. The energy intensity estimates reported herein are representative of average U.S. advanced high strength steel manufacturing; they do not represent energy consumption in any specific facility or any particular region in the United States.

3.1. Sources for Current Typical Energy Intensity

Appendix A1 presents the CT energy intensities and energy consumption for the subareas studied. Table 3-1 presents a summary of the main references consulted to identify CT energy intensity by subarea. Appendix A2 provides the references used for each subarea.

Because the steel sector is diverse, covering many products, a range of data sources were considered (see Table 3-1). In most cases, multiple references were considered for each process. Each iron and steel manufacturing facility is unique and steel is produced in different scales and by different processes; thus, it is difficult to ascertain an exact amount of energy necessary to produce a certain volume of a product. Plant size can also impact operating practices and energy efficiency. Higher efficiency is often easier to achieve in larger plants. Consequently, the values for energy intensity provided should be regarded as estimates based on the best available information.

DRAFT

Table 3-1. Main Sources Referenced in Identifying Current Typical Intensity by Subarea and Material Total

Source Abbreviation	Description
AISI 2011a	Summary for steel industry statistics, published by the American Iron and Steel Institute. The report for year 2010 is referenced.
EIA 2013a	Manufacturing Energy Consumption Survey data released by EIA every four years; this data comes from a survey that is taken by U.S. manufacturers. The most recent year for which MECS data is published is 2010. The data is scaled up to cover the entirety of U.S. manufacturing and for individual manufacturing subsectors.
EIA 2013b	Includes documentation for the model EIA utilizes to project industrial energy use.
Energetics 2000	The *Energy and Environmental Profile of the U.S. Iron and Steel Industry*, prepared by Energetics and published by DOE in 2000 provides a detailed breakdown (including total processing energy) for key process areas.
EPA 2012	This 2012 report by the Environmental Protection Agency (EPA) provides a list of energy efficiency improvement measures for use by the iron and steel industry.
IEA 2007	This 2007 report by the International Energy Agency (IEA) includes a chapter focused on iron and steel.
IPPC 2013	While this bandwidth analysis focuses on the U.S.; specific European energy consumption values or ranges are listed for select processes in this report.
NRC 2007	Provides graphics showing actual consumption at multiple Canadian plants; also addresses best available technologies.
Stubbles 2000	This report details energy consumption in the U.S. steel industry for various processes.

3.2. Current Typical Energy Intensity and Energy Consumption

Table 3-2 presents the energy intensities and calculated onsite and primary CT energy consumption for the AHSS production subareas studied. Feedstock energy is excluded from the consumption values. The energy intensities are presented in terms of Btu per lb of subarea product (listed in parenthesis in the first column). The CT energy consumption for these subareas is estimated to account for 18 TBtu of onsite energy and 24 TBtu of primary energy in 2010.

Primary energy is calculated from onsite CT energy consumption data based on an analysis of MECS data (DOE 2014), with scaling to include offsite electricity and steam generation and transmission losses (DOE 2014). To determine primary energy, the net electricity and net steam portions of sector-wide onsite energy are scaled to account for offsite generation and transmission losses and added to onsite energy (see the footnote in Table 3-2 for details on the scaling method).

DRAFT

Table 3-2. Onsite CT Energy Intensity and Calculated Energy Consumption and Calculated Primary CT Energy Consumption for U.S. AHSS Manufacturing – Application Areas Studied (2010)

Subarea (product)	Onsite CT Energy Intensity (Btu/lb product)	Production (million lb)	Onsite CT Energy Consumption, Calculated (TBtu/year)	Offsite Losses, Calculated* (TBtu/year)	Primary CT Energy Consumption, Calculated (TBtu/year)
Agglomeration (sinter)	660	178	0.12	0.02	0.13
Cokemaking (coke)	1,913	287	0.55	0.03	0.58
BF Ironmaking (iron)	5,859	914	5.51	0.06	5.57
BOF Steelmaking (raw steel)	289	1,061	0.31	0.12	0.43
EAF Steelmaking (raw steel)	980	1,681	1.65	2.92	4.57
Casting/Rolling (cast/rolled steel)					
Casting	94	2,702	0.25	0.19	0.44
Hot Rolling	1,495	2,702	4.04	1.10	5.14
Cold Rolling	1,740	2,702	5.19	2.36	7.55
Total for Process Subareas Studied			**17.62**	**6.8**	**24.41**

Current typical (CT)

* Accounts for offsite electricity and steam generation and transmission losses. Offsite electrical losses are based on published grid efficiency. EIA Monthly Energy Review, Table 2.4, lists electrical system losses relative to electrical retail sales. The energy value of electricity from offsite sources including generation and transmission losses is determined to be 10,553 Btu/kWh. Offsite steam generation losses are estimated to be 20% (Swagelok Energy Advisors, Inc. 2011. Steam Systems Best Practices) and offsite steam transmission losses are estimated to be 10% (DOE 2007, Technical Guidelines Voluntary Reporting of Greenhouse Gases and EPA 2011, ENERGY STAR Performance Ratings Methodology).

** CT energy consumption values for blast furnace and cold rolling each exclude a portion of nonfuel feedstock natural gas (based on DOE 2014).

DRAFT

4. State of the Art Energy Intensity and Energy Consumption

As plants age, manufacturing processes and equipment are updated and replaced by newer, more energy-efficient technologies. This results in a range of energy intensities among U.S. iron and steel mills. Iron and steel mills will vary widely in size, age, efficiency, energy consumption, and types and amounts of products. Modern iron and steel mills can benefit from more energy-efficient technologies and practices.

This chapter estimates the energy savings possible if U.S. AHSS producers adopt the best technologies and practices available worldwide. State of the art (SOA) energy consumption is the minimum amount of energy that could be used in a specific process using existing technologies and practices.

4.1. Sources for State of the Art Energy Intensity

Appendix A1 presents the onsite SOA energy intensity and consumption for the subareas considered in this bandwidth study. The onsite SOA energy consumption values are the net energy consumed in the process using the single most efficient process and production pathway. No weighting is given to processes that minimize waste, feedstock streams, and byproducts, or maximize yield, even though these types of process improvements can help minimize the energy used to produce a pound of product. The onsite SOA energy consumption estimates exclude feedstock energy.

Table 4-1 presents the list of published sources that were referenced to identify the SOA energy intensities. The source abbreviated as NRC 2007 was heavily referenced to determine the SOA energy intensity for many of the subareas. Technologies employed in this source are a deviant of the International Iron and Steel Institute (IISI) EcoTech Plant which includes energy-saving technologies that are both commercially available and economically attractive, with additional inclusion of certain technologies that, while less economically attractive, were being utilized commercially in Canadian steel plants.

DRAFT

Table 4-1. Main Sources Referenced in Identifying State of the Art Intensity by Process Area and Material Total

Source Abbreviation	Description
Energiron 2013	*Energiron: The Innovative Direct Reduction Technology*, Information on the direct reduction process
Giavani et al. 2012	*Consteel Evolution™ – The Second Generation of Consteel Technology*, Information regarding a specific EAF technology, the Consteel Evolution
IPPC 2013	*Best Available Techniques (BAT) Reference Document for Iron and Steel Production*, European Commission. Integrated Pollution Prevention and Control. While this bandwidth analysis focuses on the U.S., this report lists specific European energy consumption values or ranges for select processes
LBNL 2008	This Lawrence Berkeley National Laboratory report, *World Best Practice Energy Intensity Values for Selected Industrial Sector*, provides best practice values for many industrial processes, including iron and steelmaking.
NRC 2007	*Benchmarking Energy Intensity in the Canadian Steel Industry*, Natural Resources Canada. This report provides graphics and data for a variety of processes using best available technologies (energy-saving technologies that are both commercially available and economically attractive); the report also provides actual consumption at multiple Canadian plants.

4.2. State of the Art Energy Intensity and Energy Consumption

Table 4-2 presents the onsite SOA energy intensities and energy consumption for the AHSS manufacturing subareas studied. The SOA energy intensities are presented as Btu per lb or subarea product and the onsite SOA energy consumption is presented as TBtu per year.

DRAFT

Table 4-2. SOA Energy Intensities and Calculated SOA Energy Consumption for AHSS Manufacturing – Application Areas Considered

Subarea (product)	Onsite SOA Energy Intensity (Btu/lb product)	Onsite SOA Energy Consumption, Calculated (TBtu/year)
Agglomeration (sinter)	633	0.11
Cokemaking (coke)	1,684	0.48
BF Ironmaking (iron)	5,563	5.09
BOF Steelmaking (raw steel)	-151	-0.16
EAF Steelmaking (raw steel)	927	1.56
Casting/Rolling (cast/rolled steel)		
Casting	27	0.07
Hot Rolling	683	1.85
Cold Rolling	709	1.92
Total for Process Subareas Studied		**10.92**

State of the Art (SOA)

Table 4-3 presents a comparison of the onsite CT energy consumption and SOA energy consumption for each subarea and as a total. This is presented as the SOA energy savings (or *current opportunity*) and SOA energy savings percent. It is useful to consider both TBtu energy savings and energy savings percent when comparing the energy savings opportunity. Both are good measures of opportunity; however, the conclusions are not always the same. Among the processes studied, the greatest *current opportunity* in terms of percent energy savings is BOF steelmaking at 72% energy savings; the greatest *current opportunity* in terms of TBtu savings is cold rolling at 3.3 TBtu per year savings.

If U.S AHSS manufacturing (for the 2010 production level of AHSS for application areas considered) were able to attain onsite SOA energy intensities, it is estimated that 7 TBtu per year of energy could be saved from the subareas alone, corresponding to a 55% energy savings overall (see formula below). This energy savings estimate is based on adopting available SOA technologies and practices without accounting for future gains in energy efficiency from R&D. This is a simple estimate for potential savings; it is not inferred that all existing mills could achieve these state of the art values or that the improvements would prove to be cost effective in all cases.

DRAFT

Table 4-3. Calculated SOA Energy Consumption for AHSS Manufacturing – Application Areas Studied

Subarea (product)	Onsite CT Energy Consumption, Calculated (TBtu/year)	Onsite SOA Energy Consumption, Calculated (TBtu/year)	SOA Energy Savings* (CT-SOA) (TBtu/year)	SOA Energy Savings Percent** (CT-SOA)/ (CT-TM)
Agglomeration (sinter)	0.12	0.11	<0.1	19%
Cokemaking (coke)	0.55	0.48	0.07	22%
BF Ironmaking (iron)	5.51	5.09	0.42	26%
BOF Steelmaking (raw steel)	0.31	-0.16	0.47	72%
EAF Steelmaking (raw steel)	1.65	1.56	0.09	15%
Casting/Rolling (cast/rolled steel)	9.48	3.83	5.65	63%
Casting	0.25	0.07	0.18	71%
Hot Rolling	4.04	1.85	2.19	60%
Cold Rolling	5.19	1.92	3.28	64%
Total for Process Subareas Studied	**17.62**	**10.92**	**6.70**	**55%**

Current Typical (CT), State of the Art (SOA), Thermodynamic Minimum (TM)
* SOA energy savings is also called *Current Opportunity*.
** SOA energy savings percent is the SOA energy savings opportunity from transforming AHSS production processes. Energy savings percent is calculated using TM energy consumption shown in Table 6-1 as the minimum energy consumption. The energy savings percent, with TM as the minimum, is calculated as follows: (CT-SOA)/(CT-TM)

The SOA energy savings percent is the percent of energy saved with SOA energy consumption compared to CT energy consumption, while referencing the thermodynamic minimum as the baseline energy consumption. Thermodynamic minimum (TM), discussed further in Chapter 6, is considered to be equal to zero in an ideal case with perfect efficiency (i.e., energy input to a system is considered fully recoverable with no friction losses or change in surface energy). For manufacturing processes where there is an irreversible change to the material, resulting in a change to the embodied free energy content of the material (i.e., chemical reaction or permanent crystalline change due to deformation), TM is not necessarily equal to zero; in some cases the change in theoretical free energy content of the material requires energy input (TM > 0) and in other cases the change creates a theoretical free energy gain (TM < 0). Referencing TM as the baseline in comparing bandwidths of energy consumption and calculating energy savings percent provides the most accurate measure of absolute savings potential. The equation for calculating onsite SOA energy savings percent is:

$$SOA\ Savings\ \% = \frac{CT - SOA}{CT - TM}$$

DRAFT

5. Practical Minimum Energy Intensity and Energy Consumption

Technology innovation is the driving force for economic growth. Across the globe, R&D is underway that can be used to make steel in new ways and improve energy and feedstock efficiency. Commercialization of these improvements will drive the competitiveness of U.S. AHSS manufacturing. In this chapter, the R&D energy savings made possible through R&D advancements in AHSS manufacturing are estimated. Practical minimum (PM) is the minimum amount of energy required assuming the deployment of applied R&D technologies under development worldwide.

5.1. Sources for Practical Minimum Energy Intensity

In this study, PM energy intensity is the estimated minimum amount of energy consumed in a specific AHSS production process assuming that the most advanced technologies under research or development around the globe are deployed.

R&D progress is difficult to predict and potential gains in energy efficiency can depend on financial investments and market priorities. To estimate PM energy consumption for this bandwidth analysis, a search of R&D activities in the steel industry was conducted. The focus of this study's search was applied research, which was defined as investigating new technology with the intent of accomplishing a particular objective. Basic research, the search for unknown facts and principles without regard to commercial objectives, was not considered. Many of the technologies identified were disqualified from consideration due a lack of data from which to draw energy savings conclusions. Appendix A3 provides an example of the range of technologies considered for evaluation, and explains the calculation methodology.

Table 5-1 presents the key sources consulted to identify PM energy intensities in AHSS manufacturing.

Table 5-1. Sources Referenced in Identifying Practical Minimum Intensity by Process Area and Material Total

Source Abbreviation	Description
Birat et al. 2009	*The "CO_2 Tool": CO_2 emissions & energy consumption of existing & breakthrough steelmaking routes.*
Birat et al. 1999	*CO_2 Emissions and the Steel Industry's available Responses to the Greenhouse Effect.*
Energetics 2005	*Steel Industry Marginal Opportunity Study.*
Gordon et al. 2010	*Ironmaking Technology Selection for Site Specific Conditions.*
LBNL 2013	*Emerging Energy-efficiency and Carbon Dioxide Emissions-reduction Technologies for the Iron and Steel Industry.*
Sadoway 2008	*Electrochemical Pathways Towards Carbon-free Metals Production.*
UNIDO 2010	*Global Technology Roadmap for CCS in Industry: Steel Sectoral Report.*

Numerous fact sheets, case studies, reports, and other sources were referenced.

DRAFT

5.2. Practical Minimum Energy Intensity and Energy Consumption

Table 5-2 presents the onsite PM energy intensities and energy consumption for the AHSS manufacturing subareas studied. The PM energy intensities are presented as Btu per lb subarea product and the onsite PM energy consumption is presented as TBtu per year.

Table 5-2. Calculated PM Energy Consumption for AHSS Manufacturing – Application Areas Considered

Subarea (product)	Onsite PM Energy Intensity (Btu/lb product)	Onsite PM Energy Consumption, Calculated (TBtu/year)
Agglomeration (sinter)	555	0.10
Cokemaking (coke)	961	0.28
BF Ironmaking (iron)	4,462	4.08
BOF Steelmaking (raw steel)	-184	-0.19
EAF Steelmaking (raw steel)	869	1.46
Casting/Rolling (cast/rolled steel)		
Casting	22	0.06
Hot Rolling	581	1.57
Cold Rolling	578	1.56
Total for Process Subareas Studied		**8.91**

Practical Minimum (PM)

DRAFT

Table 5-3 presents a comparison of the onsite CT energy consumption and PM energy consumption for each subarea and as a total. This is presented as the PM energy savings (the difference between CT energy consumption and PM energy consumption) and PM energy savings percent. PM energy savings is equivalent to the sum of *current* and *R&D opportunity* energy savings.

It is useful to consider both TBtu energy savings and energy savings percent when comparing the energy savings opportunity. Both are good measures of opportunity; however, the conclusions are not always the same. Among the processes studied, the greatest *current* plus *R&D opportunity* in terms of percent energy savings is cokemaking at 90% energy savings; the greatest *current* plus *R&D opportunity* in terms of TBtu savings is cold rolling at 3.63 TBtu per year savings.

If U.S. AHSS manufacturing (for the 2010 production level of AHSS for application areas considered) were able to attain onsite PM energy intensities, it is estimated that 9 TBtu per year of energy could be saved from the subareas alone, corresponding to a 71% energy savings overall. This energy savings estimate is based on adopting available PM technologies and practices. This is a simple estimate for potential savings, it is not inferred that all existing mills could achieve these PM energy intensity values or that the improvements would prove to be cost effective in all cases.

Table 5-3. Calculated PM Energy Consumption for AHSS Manufacturing – Application Areas Studied

Subarea (product)	Onsite CT Energy Consumption, Calculated (TBtu/year)	Onsite PM Energy Consumption, Calculated (TBtu/year)	PM Energy Savings* (CT-PM) (TBtu/year)	PM Energy Savings Percent** (CT-PM)/ (CT-TM)
Agglomeration (sinter)	0.12	0.10	0.02	73%
Cokemaking (coke)	0.55	0.28	0.27	90%
BF Ironmaking (iron)	5.51	4.08	1.43	86%
BOF Steelmaking (raw steel)	0.31	-0.19	0.50	77%
EAF Steelmaking (raw steel)	1.65	1.46	0.19	31%
Casting/Rolling (cast/rolled steel)	9.48	3.19	6.29	70%
Casting	0.25	0.06	0.19	77%
Hot Rolling	4.04	1.57	2.47	68%
Cold Rolling	5.19	1.56	3.63	71%
Total for Process Subareas Studied	**17.62**	**8.91**	**8.70**	**71%**

Current Typical (CT), Practical Minimum (PM), Thermodynamic Minimum (TM)
* PM energy savings is the *Current Opportunity* plus the *R&D Opportunity.*
** PM energy savings percent is the PM energy savings opportunity from transforming AHSS production processes. Energy savings percent is calculated using TM energy consumption shown in Table 6-1 as the minimum energy consumption. The energy savings percent, with TM as the minimum, is calculated as follows: (CT-PM)/(CT-TM)

The PM energy savings percent is the percent of energy saved with PM energy consumption compared to CT energy consumption, while referencing the thermodynamic minimum as the baseline energy consumption. Thermodynamic minimum (TM), discussed further in the following section, is considered to be equal to zero in an ideal case with perfect efficiency (i.e., energy input to a system is considered fully recoverable with no friction losses or change in surface energy). For manufacturing processes where there is an irreversible change to the material, resulting in a change to the embodied free energy content of the material (i.e., chemical

DRAFT

reaction or permanent crystalline change due to deformation), TM is not necessarily equal to zero; in some cases the change in theoretical free energy content of the material requires energy input (TM > 0) and in other cases the change creates a theoretical free energy gain (TM < 0). Referencing TM as the baseline in comparing bandwidths of energy consumption and calculating energy savings percent provides the most accurate measure of absolute savings potential. The equation for calculating onsite PM energy savings percent is:

$$PM\ Savings\ \% = \frac{CT - PM}{CT - TM}$$

DRAFT

6. Thermodynamic Minimum Energy Intensity and Energy Consumption

Real world iron and steel production does not occur under theoretically ideal conditions; however, understanding the theoretical minimal amount of energy required to manufacture AHSS can provide a more complete understanding of the realistic opportunities for energy savings. This baseline can be used to establish more realistic projections (and bounds) for the future R&D energy savings that may be achieved. This chapter presents the thermodynamic minimum (TM) energy consumption required for the subareas studied.

TM energy consumption, which is based on Gibbs free energy (ΔG) calculations, assumes ideal conditions that are unachievable in real-world applications. TM energy consumption assumes that all energy is used productively, that there are no energy losses, and that energy is ultimately perfectly conserved by the system (i.e., when cooling a material to room temperature or applying work to a process, the heat or work energy is fully recovered – perfect efficiency). It is not anticipated that any manufacturing process would ever attain this value in practice. A reasonable long-term goal for energy efficiency would be the practical minimum (see Chapter 5).

For manufacturing processes where there is an irreversible change to the material, resulting in a change to the embodied free energy content of the material (i.e., chemical reaction or permanent crystalline change due to deformation), TM is not necessary equal to zero; in some cases the change in theoretical free energy content of the material requires energy input (TM > 0) and in other cases the change creates a theoretical free energy gain (TM < 0).

6.1. Sources for Thermodynamic Minimum Energy Intensity

The thermodynamic minimum energy intensity was calculated for each sub-process by determining the Gibbs free energy associated with the chemical transformations involved, under ideal conditions for a manufacturing process. [8] The TM energy intensity is *negative* when the chemical reaction is net-exergonic and *positive* when the chemical reaction is net-endergonic. [9] Changes in surface energy were not considered in the TM analysis. The change in entropy was calculated based on the relative change in the number of molecules, and the change in enthalpy was calculated based on the change in bond energy. [10]

The main source for the AHSS production subarea thermodynamic minimum energy intensities are the 2000 report *Theoretical Minimum Energies to Produce Steel for Selected Conditions* by Fruehan et al. This report highlights minimum values based on theoretical models and specific compositions, and is derived from earlier work conducted by Carnegie Mellon University for the

[8] Unless otherwise noted, "ideal conditions" means a pressure of 1 atmosphere and a temperature of 77°F.
[9] Exergonic (reaction is favorable) and endergonic (reaction is not favorable) are thermodynamic terms for total change in Gibbs free energy (delta G). This differs from exothermic (reaction is favorable) and endothermic (reaction is not favorable) terminology that are used in describing change in enthalpy (delta H).
[10] Note that the bond energy values are averages, not specific to the molecule in question.

DRAFT

DOE. In addition to basing the TM energy intensity values on internal calculations, the 1998 source *Future Technologies for Energy-Efficient Iron and Steel Making* by de Beer, Worrell, and Blok and which discusses theoretical values was consulted.

The TM energy intensity calculation is path independent (state function), but is directly related to the relative energy levels of the substrate reactants and the products. The reported value depends only on the starting material and the end product, and would not change if the process had greater or fewer process steps. It is important to note that a negative TM value does not imply that the reaction will occur without being forced by a manufacturing process.

BOF steelmaking can at times result in net energy gain through exothermic processes. For exergonic iron and steel manufacturing processes, a zero baseline would result in negative percent savings, a physical impossibility.

In this report, TM energy consumption is referenced as the baseline (or minimum amount of energy) when calculating the absolute energy savings potential. The equations used to determine the absolute energy savings for SOA and PM are as follows:

$$SOA\ Savings\ \% = \frac{CT - SOA}{CT - TM}$$

$$PM\ Savings\ \% = \frac{CT - PM}{CT - TM}$$

For processes requiring an energy intensive transformation (e.g., blast furnace ironmaking), this percent energy savings approach results more realistic and comparable energy savings estimates. Using zero as the baseline (or minimum amount of energy) would exaggerate the total bandwidth to which SOA energy savings and PM energy savings are compared to determine the energy savings percent. When TM energy consumption is referenced as the baseline, SOA energy savings and PM energy savings are relatively more comparable, resulting in more accurate energy savings percentages.

TM energy intensity is the least amount of energy required for each of the six process areas examined in this report: ore agglomeration, cokemaking, ironmaking, BOF steelmaking, EAF steelmaking, and casting and rolling. The full credit of off-gas chemical and thermal energy is considered.

6.2. Thermodynamic Minimum Energy Intensity and Energy Consumption

The minimum baseline of energy consumption for an AHSS production subarea is its TM energy consumption. If the 2010 level of AHSS production occurred at TM energy intensity, there would be 100% savings. The percentage of energy savings is determined by calculating the

DRAFT

decrease in energy consumption and dividing it by the total possible savings (CT energy consumption-TM energy consumption).

Table 6-1 provides the TM energy intensities and energy consumption for the subareas studied (excluding feedstock energy). It is important to keep in mind that ideal conditions are unrealistic goals in practice and these values serve only as a guide to estimating energy savings opportunities. As mentioned, the TM energy consumption was used to calculate the *current* and *R&D* energy savings percentages (not zero).

Table 6-1. Calculated TM Energy Consumption for AHSS Manufacturing – Application Areas Considered

Subarea (product)	TM Energy Intensity (Btu/lb product)	TM Energy Consumption, Calculated (TBtu/year)
Agglomeration (sinter)	516	0.09
Cokemaking (coke)	860	0.25
BF Ironmaking (iron)	4,215	3.85
BOF Steelmaking (raw steel)	-322	-0.34
EAF Steelmaking (raw steel)	620	1.04
Casting/Rolling (cast/rolled steel)		
Casting	<0.01	0.00
Hot Rolling	147	0.40
Cold Rolling	22	0.06
Total for Process Subareas Studied		**5.35**

Thermodynamic minimum (TM)

DRAFT

7. Current and R&D Opportunity Analysis/Bandwith Summary

Table 7-1 presents the *current opportunity* and *R&D opportunity* energy savings for the subareas studied considering the AHSS production for the application area boundary considered for this study. Each row in Table 7-1 shows the opportunity bandwidth for a specific AHSS manufacturing subarea and as a total.

As shown in Figure 7-1, two hypothetical opportunity bandwidths for energy savings are estimated (as defined in Chapter 1). To complete the subareas studied, the analysis shows the following:

- *Current Opportunity* – 7 TBtu per year of energy savings could be obtained if state of the art technologies and practices are deployed.
- *R&D Opportunity* – 2 TBtu per year of additional energy savings could be attained in the future if applied R&D technologies under development worldwide are deployed (i.e., reaching the practical minimum).

Figure 7-1 also shows the estimated *current* and *R&D* energy savings opportunities for individual AHSS manufacturing subareas. The area between *R&D opportunity* and *impractical* is shown as a dashed line with color fading because the PM energy savings impacts are speculative and based on unproven technologies.

DRAFT

Table 7-1. Current and R&D Opportunity for AHSS Manufacturing – Application Areas Studied

Subarea (product)	Current Opportunity (CT-SOA) (TBtu/year)	R&D Opportunity (SOA-PM) (TBtu/year)
Agglomeration (sinter)	<0.01	0.01
Cokemaking (coke)	0.07	0.21
BF Ironmaking (iron)	0.42	1.01
BOF Steelmaking (raw steel)	0.47	0.10
EAF Steelmaking (raw steel)	0.09	0.32
Casting/Rolling (rolled steel)		
Casting	0.18	0.01
Hot Rolling	2.19	0.27
Cold Rolling	3.28	0.35
Total for Process Subareas Studied	**6.70**	**2.00**

Current typical (CT), state of the art (SOA), practical minimum (PM)

DRAFT



Figure 7-1. Current and R&D Energy Savings Opportunities in U.S. AHSS Manufacturing for the Subareas and Application Areas Studied

From the subareas studied, the greatest *current* energy savings opportunity comes from upgrading cold rolling and the greatest *R&D* energy savings opportunity comes from upgrading blast furnace ironmaking.

The *impractical* bandwidth represents the energy savings potential that would require fundamental changes in AHSS manufacturing. It is the difference between PM energy consumption and TM energy consumption. The term *impractical* is used because the significant research investment required based on today's knowledge would no longer be practical because of the thermodynamic limitations. The TM energy consumption is based on ideal conditions that are typically unattainable in commercial applications. It was used as the baseline for calculating the energy savings potentials (not zero) to provide more accurate targets of energy savings opportunities.

DRAFT

8. References

AEHOF 2013 — "ACIPCO's 65-MW Contiarc Furnace." Alabama Engineering Hall of Fame (AEHOF). 2013. http://aehof.eng.ua.edu/members/acipcos-65-megawatt-contiarc-furnace/

AISI 2011a — *2010 Annual Statistical Report.* American Iron and Steel Institute (AISI). 2011.

AISI 2011b — *Profile of the American Iron and Steel Institute 2010-2011*. American Iron and Steel Institute (AISI). 2011. http://www.steel.org/~/media/Files/AISI/About%20AISI/Profile%20Brochure%20F-singles_CX.pdf

AISI 2012 — *Profile of the American Iron and Steel Institute 2012*. American Iron and Steel Institute (AISI). 2012. http://www.steel.org/~/media/Files/AISI/Reports/2012%20Profile%20F4-SDMIcrx-sm.pdf

AISI 2013a — "2013 Steel Industry Profile." American Iron and Steel Institute (AISI). 2013. http://www.steel.org/About%20AISI/Industry%20Profile.aspx

AISI 2013b — "Steelmaking Flowlines." American Iron and Steel Institute (AISI). 2013. http://www.steel.org/Making%20Steel/How%20Its%20Made/Steelmaking%20Flowlines.aspx

AISI 2015 — Data on presentation slide provided by AISI. 2015.

AIST 2011 — *2011 Electric Arc Furnace Roundup.* Association for Iron & Steel Technology (AIST). 2011.

APP 2010 — *The State–of-the-Art Clean Technologies (SOACT) for Steelmaking Handbook, 2nd Edition*. Asia Pacific Partnership on Clean Development and Climate (APP). 2010. www.asiapacificpartnership.org/pdf/Projects/Steel/SOACT-Handbook-2nd-Edition.pdf

ArcelorMittal 2012 — "Steel Industry Statistics." ArcelorMittal. 2012. http://www.transformingarcelormittalusa.com/USASteelIndustry/AmericasSteelIndustryStatistics.aspx

Arvedi et al. 2008 — "The Arvedi endless strip production line (ESP) from liquid steel to hot-rolled coil in seven minutes." Arvedi, G., Mazzolari, F., Bianchi, A., Holleis, G., Siegl, J, & Angerbauer, A. *La Revue de Métallurgie-CIT* (July/August): 398–407. 2008.

Barati et al. 2011 — "Energy recovery from high temperature slags." Barati, M., S. Esfahani, & T. A. Utigard. *Energy* 36(9): 5440–49. 2011.

DRAFT

Beraldo et al. 2003	"Implementation of Cold Tundish at CTS Continuous Casting Process." Beraldo, A.K., Moreira, D.B., Duarte, J.C., Matos, M.F., & Nascimento, Z.D. La Revue de Métallurgie-CIT. October, 955-960. 2003.
Birat et al. 1999	"CO_2 Emissions and the Steel Industry's available Responses to the Greenhouse Effect." Birat, J.-P., Vizioz, J.-P., de Lassat, Y., Schneider, M., & Jeanneau, M. *IRSID*. 1999. http://www.ulcos.org/en/docs/Ref16%20-%20Sdiego.pdf
Birat et al. 2009	"The "CO_2 Tool": CO_2 emissions & energy consumption of existing & breakthrough steelmaking routes." Birat, J.-P., Lorrain, J.-P., de Lassat, Y. *La Revue de Metallurgie*, *106* (09): 325-336.
BMWi 2008	*Climate Protection and Energy Efficiency: Research, Development and Demonstration of Modern Energy Technologies.* German Federal Ministry of Economics and Technology (BMWi). 2008. www.bmwi.de/English/Redaktion/Pdf/climate-protection-energy-efficiency,property=pdf,bereich=bmwi,sprache=en,rwb=true.pdf
Considine 2012	*Economic Impacts of the American Steel Industry*. Considine, T.J. 2012. http://legacy.steel.org/news/NewSteelNews/images/PDFs/Considine_March%202012.pdf
de Beer et al. 1998	*Future Technologies for Energy-Efficient Iron and Steel Making*. de Beer, J., Worrell, E., & Blok, K. *Annu. Rev. Energy Environ. 23*:123-205. 1998.
Demeri 2013	*Advanced High-Strength Steels: Science, Technology, and Applications.* Demeri, Mahmoud Y. ASM International: Materials Park, OH. 2013.
DOE 2002	*Recycling and Reuse of BOF/BOP Steelmaking Slags.* U.S. Department of Energy (DOE) Office of Industrial Technology (OIT). 2002. www.energy.gov/sites/prod/files/2014/05/f16/recycling_bof.pdf
DOE 2005	*Process to Continuously Melt, Refine, and Cast High Quality Steel.* U.S. Department of Energy (DOE) Industrial Technologies Program (ITP). 2005. www.energy.gov/sites/prod/files/2014/05/f16/dev_of_process.pdf
DOE 2010	*IMPACTS: Industrial Technologies Program: Summary of Program Results for CY 2009*. U.S. Department of Energy (DOE) Industrial Technologies Program (ITP). 2010. www1.eere.energy.gov/manufacturing/about/pdfs/impacts2009_full_report.pdf
DOE 2011	*Grand Challenge Portfolio: Driving Innovations in Industrial Energy Efficiency*. U.S. Department of Energy (DOE), Industrial Technologies Program (ITP). 2011. www1.eere.energy.gov/manufacturing/pdfs/grand_challenges_portfolio.pdf

DRAFT

DOE 2013 "Energy Savings Assessments (ESA)." Conducted by the U.S. Department of Energy (DOE) and Oak Ridge National Laboratory (ORNL) between 2006 and 2011. Results obtained from personal communications with Sachin Nimbalkar, Oak Ridge National Laboratory.

DOE 2014 *Manufacturing Energy and Carbon Footprints.* U.S. Department of Energy, Advanced Manufacturing Office. 2014. http://energy.gov/eere/amo/manufacturing-energy-and-carbon-footprints-2010-mecs

DOE 2015a *Bandwidth Study on Energy Use and Potential Energy Saving Opportunities in U.S. Chemical Manufacturing.* U.S. Department of Energy, Advanced Manufacturing Office. Prepared by Energetics Incorporated. 2015. http://energy.gov/sites/prod/files/2015/08/f26/chemical_bandwidth_report.pdf

DOE 2015b *Bandwidth Study on Energy Use and Potential Energy Saving Opportunities in U.S. Iron and Steel Manufacturing.* U.S. Department of Energy, Advanced Manufacturing Office. Prepared by Energetics Incorporated. 2015. http://energy.gov/sites/prod/files/2015/08/f26/iron_and_steel_bandwidth_report_0.pdf

DOE 2015c *Bandwidth Study on Energy Use and Potential Energy Saving Opportunities in U.S. Petroleum Refining.* U.S. Department of Energy, Advanced Manufacturing Office. Prepared by Energetics Incorporated. 2015. http://energy.gov/sites/prod/files/2015/08/f26/petroleum_refining_bandwidth_report.pdf

DOE 2015d *Bandwidth Study on Energy Use and Potential Energy Saving Opportunities in U.S. Pulp and Paper Manufacturing.* U.S. Department of Energy, Advanced Manufacturing Office. Prepared by Energetics Incorporated. 2015. http://energy.gov/sites/prod/files/2015/08/f26/pulp_and_paper_bandwidth_report.pdf

EIA 2009 "Manufacturing Energy and Consumption Survey (MECS) 2006." U.S. Energy Information Administration. 2009. http://www.eia.gov/consumption/manufacturing/data/2006/

EIA 2013a "Manufacturing Energy and Consumption Survey (MECS) 2010." U.S. Energy Information Administration (EIA). 2013. http://www.eia.gov/consumption/manufacturing/data/2010/

EIA 2013b *Model Documentation Report: Industrial Demand Module of the National Energy Modeling System.* U.S. Energy Information Administration (EIA). 2013. http://www.eia.gov/forecasts/nemsdoc/industrial/pdf/m064(2012).pdf

DRAFT

Energetics 2000	*Energy and Environmental Profile of the U.S. Steel Industry*. Energetics, Inc. for U.S. Department of Energy, Office of Industrial Technologies. 2000. http://energy.gov/sites/prod/files/2013/11/f4/steel_profile.pdf
Energetics 2004	*Steel Industry Energy Bandwidth Study*. Energetics, Inc. for U.S. Department of Energy, Industrial Technologies Program. 2004. http://energy.gov/sites/prod/files/2013/11/f4/steelbandwidthstudy.pdf
Energetics 2005	*Steel Industry Marginal Opportunity Study*. Energetics, Inc. for U.S. Department of Energy, Industrial Technologies Program. 2005. http://energy.gov/sites/prod/files/2013/11/f4/steelmarginalopportunity.pdf
Energiron 2013	"Energiron: The Innovative Direct Reduction Technology." Energiron. 2013. http://www.energiron.com/
EPA 2011	"Location of U.S. Facilities." U.S. Environmental Protection Agency (EPA). 2011. http://www.epa.gov/sectors/sectorinfo/sectorprofiles/ironsteel/map.html
EPA 2012	*Available and Emerging Technologies for Reducing Greenhouse Gas Emissions from the Iron and Steel Industry.* U.S. Environmental Protection Agency (EPA). 2012. http://www.epa.gov/nsr/ghgdocs/ironsteel.pdf
Fruehan et al. 2000	*Theoretical Minimum Energies to Produce Steel for Selected Conditions*. Fruehan, R.J., Fortini, O., Paxton, H.W., and Brindle, R. for the U.S. Department of Energy Office of Industrial Technologies. 2000. http://energy.gov/sites/prod/files/2013/11/f4/theoretical_minimum_energies.pdf
Giavani et al. 2012	"Consteel® Evolution™ – The Second Generation of Consteel Technology." Giavani, C., Malfa, E., & Memoli, F. *Industrial Heating.* 2012. http://www.industrialheating.com/articles/90594-consteel-evolution---the-second-generation-of-consteel-technology
Gordon et al. 2010	*Ironmaking Technology Selection for Site Specific Conditions*. Gordon, Y., Freislich, M., & Els, J. AISTech 2010 Proceedings – Volume I: 519-528. 2010.
Griggs 2013	"Nucor's La. plant near completion." Griggs, T. *The Advocate*. 2013. http://theadvocate.com/home/6552645-125/nucors-la-plant-near-completion
GTI 2011	*Final Technical Report: Advanced Energy and Water Recovery Technology from Low Grade Waste Heat.* Gas Technology Institute (GTI). 2011. www.osti.gov/bridge/servlets/purl/1031483/1031483.pdf
IEA 2007	*Tracking Industrial Energy Efficiency and CO_2 Emissions*. International Energy Agency (IEA). 2007. http://www.iea.org/publications/freepublications/publication/tracking_emissions.pdf

DRAFT

IMP 2006 — *Verification of Steelmaking Slag Iron Content, Final Technical Progress Report.* DE-FC36-01ID14046. Institute of Materials Processing (IMP), Michigan Technological University. 2006. www.ntis.gov/assets/pdf/st-on-cd/DE2006892748.pdf

Inoue 1995 — "The Steel Industry in Japan: Progress in Continuous Casting." In *Energy Efficiency Utilizing High Technology: As Assessment of Energy Use in Industry and Buildings, Appendix A: Case Studies*. Inoue, K. 1995.

IPPC 2001 — *Reference Document on Best Available Techniques for the Production of Iron and Steel.* European Union. Integrated Pollution Prevention and Control Bureau (IPPC). 2001.

IPPC 2013 — *Best Available Techniques (BAT) Reference Document for Iron and Steel Production*. European Commission. Integrated Pollution Prevention and Control (IPPC). 2013. http://eippcb.jrc.ec.europa.eu/reference/BREF/IS_Adopted_03_2012.pdf

JISF 2012 — "Technologies to Reduce CO_2 Emissions." Japan Iron and Steel Federation (JISF). 2012. www.jisf.or.jp/course50/tecnology01/index_en.html

KR Tec n.d. — *Environmental Preheating and Continuous Charging System (EP)*. KR Tec and CVS Technology. n.d.

LBNL 2000 — *Emerging Energy-Efficient Industrial Technologies*. Martin, N., Worrell, E., Ruth, M., Price, L., Elliott, R.N., Shipley, A.M., & Thorne, J. for Lawrence Berkeley National Laboratory (LBNL). 2000.

LBNL 2008 — *World Best Practice Energy Intensity Values for Selected Industrial Sectors*. Worrell, E., Price, L., Neelis, M., Galitsky, C., & Nan, Z. for Lawrence Berkeley National Laboratory (LBNL). 2008. http://ies.lbl.gov/sites/all/files/industrial_best_practice_en_0.pdf

LBNL 2010a — *Development of Bottom-up Representation of Industrial Energy Efficient Technologies in Integrated Assessment Models for the Iron and Steel Sector.* Xu, T., Sathaye, J., & Galitsky, C. for Lawrence Berkeley National Laboratory (LBNL). 2010. http://ies.lbl.gov/sites/all/files/lbnl-4314e_0.pdf

LBNL 2010b — *Energy Efficiency Improvement and Cost Saving Opportunities for the Iron and Steel Industry: An ENERGY STAR Guide for Energy and Plant Managers*. Neelis, M., Worrell, E., & Masanet, E. for Lawrence Berkeley National Laboratory (LBNL). 2010. http://ies.lbl.gov/sites/all/files/lbnl-4779e_0.pdf

DRAFT

LBNL 2013	*Emerging Energy-efficiency and Carbon Dioxide Emissions-reduction Technologies for the Iron and Steel Industry*. Hasanbeigi, A., Price, L., & Arens, M. for Lawrence Berkeley National Laboratory (LBNL). 2013. http://china.lbl.gov/sites/all/files/6106e-steel-tech.pdf
Marcus 2013	*AutoBody Warfare: Aluminum Attack*. Marcus, P. F. World Steel Dynamics. October 2013. http://www.a-sp.org/~/media/Files/Autosteel/Research/10-04-2014%20-%20AutoWarfare%20Executive%20Summary.pdf?la=en
McGannon 1971	*The Making, Shaping and Treating of Steel*, 9th ed. McGannon, H. E. 1971.
Nashan 2007	*Strategies to Increase the Technical and Economic Efficiency of the Blast Furnace Ironmaking Process by Using New Advanced Cokemaking Technologies*. Nashan, G. 2007. www.coke-oven-managers.org/PDFs/2007/2007%20-%20Nashan.pdf
NEDO 2008	*Global Warming Countermeasures: Japanese Technologies for Energy Savings/GHG Emissions Reduction, 2008 Revised Edition*. New Energy and Industrial Technology Development Organization (NEDO). 2008. www.nedo.go.jp/content/100107259.pdf
NRC 2007	*Benchmarking Energy Intensity in the Canadian Steel Industry*. Prepared by the Canadian Industry Program for Energy Conservation for Canadian Steel Producers Association and Natural Resources Canada (NRC). 2007. http://oee.nrcan.gc.ca/sites/oee.nrcan.gc.ca/files/pdf/industrial/technical-info/benchmarking/csi/documents/SteelBenchmarkEnglish.pdf
NSF 2007	"Table 50: Funds for industrial R&D as a percent of net sales of companies performing industrial R&D in the United States, by industry and company size: 2007." *Industrial Research and Development Information System.* National Science Foundation (NSF). http://www.nsf.gov/statistics/iris/tables.cfm?pub_year=nsf_2007
Peaslee et al. 2006	*Development of a Process to Continuously Melt, Refine and Cast High Quality Steel. Final Technical Report*. Peaslee K. D., Richards, V.L., Robertson, D.G.C., & Smith. J.D. for the U.S. Department of Energy. 2006. www.energy.gov/sites/prod/files/2014/05/f16/dev_of_process.pdf
POSCO 2010	*Carbon Report 2010.* Pohang Iron & Steel Co, Ltd. Pohang Iron & Steel Co, Ltd. (POSCO). 2010.
Rummler et al. n.d.	"New Generation in preheating technology for electric steel making - higher productivity with reduced power." Rummler, K., Tunaboylu, A. & Ertas, D. Sundheim, Germany: KR Tech GMBH. n.d.

DRAFT

Sadoway 2008	"Electrochemical Pathways Towards Carbon-free Metals Production." Sadoway, D.R. Presentation. 2008. http://gcep.stanford.edu/pdfs/2RK4ZjKBF2f71uM4uriP9g/SadowayGCEP_reduced.pdf
SRI 2013a	"Steel Recycling Institute." Steel Recycling Institute (SRI). 2013. http://www.recycle-steel.org
SRI 2013b	"Steel Recycling Rates." Steel Recycling Institute (SRI). 2013. http://www.recycle-steel.org/Recycling%20Resources/Steel%20Recycling%20Rates.aspx
Steel Dynamics, Inc. n.d.	*Welcome to Mesabi Nugget.* Presentation. n.d. http://www.mesabinuggetmn.com/pdf/mesabinuggetoverview.ppt
Stelco 1993	*Present and Future Use of Energy in the Canadian Steel Industry*. Ottawa, Canada: CANMET. Stelco. 1993.
Stubbles 2000	*Energy Use in the U.S. Steel Industry: An Historical Perspective and Future Opportunities*. Stubbles, J. for the U.S. Department of Energy, Office of Industrial Technologies. 2000. http://energy.gov/sites/prod/files/2013/11/f4/steel_energy_use.pdf
Thekdi 2010	*Development of Next Generation Heating System For Scale Free Steel Reheating-Final Technical Report*. Thekdi, A. for the U.S Department of Energy. 2010. www.osti.gov/scitech/servlets/purl/1004059
UNIDO 2010	*Global Technology Roadmap for CCS in Industry: Steel Sectoral Report*. Birat, JP for the United Nations Industrial Development Organization (UNIDO). 2010. http://cdn.globalccsinstitute.com/sites/default/files/publications/15671/global-technology-roadmap-ccs-industry-steel-sectoral-report.pdf
USCB 2012	"North American Industry Classification System." United States Census Bureau (USCB). 2012. http://www.census.gov/eos/www/naics/index.html
USGS 2012a	*2010 Minerals Yearbook: Iron and Steel [Advance Release]*. U.S. Geological Survey (USGS). 2012. http://minerals.usgs.gov/minerals/pubs/commodity/iron_&_steel/myb1-2010-feste.pdf
USGS 2012b	*Mineral Commodity Summaries, January 2012: Iron and Steel*. Prepared by Fenton, M.D. for the U.S. Geological Survey (USGS). 2012. http://minerals.er.usgs.gov/minerals/pubs/commodity/iron_&_steel/mcs-2012-feste.pdf

DRAFT

USGS 2012c	*2010 Minerals Yearbook: Iron and Steel Scrap [Advance Release]*. U.S. Geological Survey (USGS). 2012. http://minerals.usgs.gov/minerals/pubs/commodity/iron_%26_steel_scrap/myb1-2010-fescr.pdf
Voestalpine 2013	"Voestalpine constructing direct reduction plan in Texas, USA." Voestalpine. 2013. http://www.voestalpine.com/group/en/press/press-releases/2013-03-13-voestalpine-constructing-direct-reduction-plant-in-texas-usa.html
WCA 2013	"Coal & Steel." World Coal Association (WCA). 2013. http://www.worldcoal.org/coal/uses-of-coal/coal-steel
Worrell & Reuter 2014	*Handbook of Recycling: State-of-the-Art for Practitioners, Analysts, and Scientists*. Worrell, E. & M.A. Reuter. 2014. United States of America: Elsevier, Inc.
WSA 2012	*Sustainable Steel: At the core of a green economy*. World Steel Association (WSA). 2012. http://www.worldsteel.org/dms/internetDocumentList/bookshop/Sustainable-steel-at-the-core-of-a-green-economy/document/Sustainable-steel-at-the-core-of-a-green-economy.pdf
WSA 2014	*Fact Sheet: Advanced steel applications.* World Steel Association (WSA). October 2014. http://www.worldsteel.org/publications/fact-sheets/content/04/text_files/file0/document/fact_Advanced%20steel%20applications_2014.pdf

DRAFT

Appendix A1. Master AHSS Summary Table

Table A1. U.S. Production Volume of AHSS Processes in 2010 with Energy Intensity Estimates and Calculated Onsite Energy Consumption for the Four Bandwidth Measures (Excludes Feedstock Energy)

Subarea (product)	2010 Application Area Production (million lb)	Onsite Energy Intensity (Btu/lb product)				Calculated Onsite Energy Consumption (TBtu/year)			
		CT	SOA	PM	TM	CT	SOA	PM	TM
Agglomeration (sinter)	178	660	633	555	516	0.12	0.11	0.10	0.09
Cokemaking (coke)	287	1,913	1,684	961	860	0.55	0.48	0.28	0.25
BF Ironmaking (iron)	914	5,859	5,563	4,462	4,215	5.51*	5.09	4.08	3.85
BOF Steelmaking (raw steel)	1,061	289	-151	-184	-322	0.31	-0.16	-0.19	-0.34
EAF Steelmaking (raw steel)	1,681	928	811	618	571	1.56	1.36	1.04	0.96
Casting/Rolling (cast/rolled steel)						*9.48**	*3.83*	*3.19*	*0.46*
Casting	2,702	94	27	22	<0.01	0.25	0.07	0.06	0.00
Hot Rolling	2,702	1,495	683	581	147	4.04	1.85	1.57	0.40
Cold Rolling	2,702	1,740	709	578	22	5.19*	1.92	1.56	0.06

* Current typical values for blast furnace ironmaking and cold rolling each exclude a portion of nonfuel feedstock natural gas

The four bandwidth measures are current typical (CT), state of the art (SOA), practical minimum (PM), and thermodynamic minimum (TM).

DRAFT

Appendix A2: References for Production, CT, SOA, PM, TM

Table A2. U.S. Production Volume of AHSS Processes in 2010 with Energy Intensity Estimates and Calculated Onsite Energy Consumption for the Four Bandwidth Measures (Excludes Feedstock Energy)

Subarea	Production Reference(s)	CT Energy Intensity Reference(s)	SOA Energy Intensity Reference(s)	TM Energy Intensity Reference(s)
Agglomeration (sinter)	Estimated based on AISI 2011a, Demeri 2013	IPPC 2013	LBNL 2008	Fruehan et al. 2000
Cokemaking (coke)	Estimated based on AISI 2011a, Demeri 2013	AISI 2011a; EIA 2013b	NRC 2007	Fruehan et al. 2000
BF Ironmaking (iron)	Estimated based on AISI 2011a, Demeri 2013	AISI 2011a; IPPC 2013	NRC 2007	Fruehan et al. 2000
BOF Steelmaking (raw steel)	Estimated based on AISI 2011a, Demeri 2013	IPPC 2013	NRC 2007	Fruehan et al. 2000
EAF Steelmaking (raw steel)	Estimated based on AISI 2011a, Demeri 2013	AIST 2011	NRC 2007; Giavani et al. 2012	Fruehan et al. 2000
Casting/Rolling (cast/rolled steel)				
Casting	Estimated based on AISI 2011a, AISI 2015, Demeri 2013	NRC 2007	NRC 2007; LBNL 2008	Fruehan et al. 2000
Hot Rolling	Estimated based on AISI 2011a, AISI 2015, Demeri 2013	NRC 2007	NRC 2007	Fruehan et al. 2000
Cold Rolling	Estimated based on AISI 2011a, AISI 2015, Demeri 2013	EIA 2013b	LBNL 2008	Fruehan et al. 2000

The four bandwidth measures are current typical (CT), state of the art (SOA), practical minimum (PM), and thermodynamic minimum (TM)

DRAFT

Appendix A3: Practical Minimum Energy Intensity Calculation and Technologies Considered

To estimate PM energy consumption for this bandwidth analysis, a broad search of R&D activities in the iron and steel industry was conducted. A large number and range of potential technologies were identified. If more than one technology was considered for a particular process, the technology that resulted in the lowest energy intensity was conservatively selected for the PM energy intensity. The onsite PM energy intensity and consumption values are shown in Table A3 below.

Table A3. Calculated PM Energy Consumption for AHSS Manufacturing – Application Areas Considered

Subarea (product)	Onsite PM Energy Intensity (Btu/lb product)	Onsite PM Energy Consumption, Calculated (TBtu/year)
Agglomeration (sinter)	555	0.10
Cokemaking (coke)	961	0.28
BF Ironmaking (iron)	4,462	4.08
BOF Steelmaking (raw steel)	-184	-0.19
EAF Steelmaking (raw steel)	869	1.46
Casting/Rolling (cast/rolled steel)		
Casting	22	0.06
Hot Rolling	581	1.57
Cold Rolling	578	1.56
Total for Process Subareas Studied		**8.91**

Practical Minimum (PM)

DRAFT

The PM energy intensity for AHSS manufacturing was determined based on the technologies outlined in Table A4. The applicability column indicates the subarea/sub-process where the technology is considered for application. The percent savings over the PM baseline is estimated, along with a brief explanation. Some technologies in Table A4 were considered but not included in the final PM model (in most of the cases the savings estimates were too conservative). In some cases, likely due to the conservative estimates of researchers, the estimated PM energy intensity was higher than the SOA energy intensity. For these cases, the crosscutting technology savings estimates were utilized. R&D in some process areas is more broadly applicable, such as utility/power generation improvements and crosscutting technologies. Cross-cutting technologies applied during the PM analysis included new high-temperature, low-cost ceramic media for natural gas combustion burners, advanced energy and water recovery technology from low-grade waste heat, and control systems for recycling steel residues. The estimated energy savings from crosscutting improvements were assumed to be applicable to all six processes studied. To calculate PM energy intensity, the SOA energy intensity and TM energy intensity were multiplied by the combined estimated savings for crosscutting improvements (19%) and subtracted from the SOA energy consumption:

$$PM = SOA - (SOA - TM) * (19\%)$$

Table A5 provides a more comprehensive list of some of the technologies considered in studying R&D technology opportunities for AHSS manufacturing.

Table A4. Details of PM Technologies Considered

Technology Name	Description	Applicability	Explanation of energy savings assumptions	PM Energy Intensity (Btu/lb) or Percent savings (over baseline energy)	Included in PM model?	Reason for excluding (if applicable)	Reference
Single-chamber-system coking reactors	Replace series of coking ovens with a single large volume oven	Cokemaking	Thermal efficiency improvement from 38% to 70%	1,186 Btu/lb	Yes		Díez et al. 2002, IPPC 2001, EPA 2012, Nashan 2007, LBNL 2010b
Coal Moisture Control	Drying of coal with waste heat gases	Cokemaking	Fuel savings of 0.3 GJ/tonne	1,778 Btu/lb	No	Single-chamber-system coking reactors provides a lower baseline energy use.	APP 2010

DRAFT

Technology Name	Description	Applicability	Explanation of energy savings assumptions	PM Energy Intensity (Btu/lb) or Percent savings (over baseline energy)	Included in PM model?	Reason for excluding (if applicable)	Reference
Top Pressure Recovery Turbines	Uses hot high pressure gas from the furnace to power a turbine; dust removal from blast furnace gases using dry and wet methods.	BF Ironmaking	Turbine could produce additional 14-36 kWh/ton of hot metal (depending on available pressure)	5,811 Btu/lb	No	Drum chute and segregation slit charging provides a lower baseline energy use.	APP 2010, EPA 2012, Inoue 1995, NEDO 2008, Stelco 1993
Drum Chute and Segregation Slit Charging	Use of a drum chute and segregation slit wire to control the particles dropping into the furnace	BF Ironmaking	Can decrease coke use by 0.7 MMBtu/ton	5,509 Btu/lb	Yes		EPA 2012, NEDO 2008, LBNL 2010b
Heat recovery from blast furnace slag	Capture of embedded heat in blast furnace slag through recovery as hot air or steam, chemical energy, or thermoelectric power.	BF Ironmaking	Savings of approximately 0.35 GJ/tonne of pig iron	5,709 Btu/lb	No	Drum chute and segregation slit charging provides a lower baseline energy use.	Barati et al. 2011, IPPC 2013, JISF 2012, LBNL 2010b, POSCO 2010
Recycling and reuse of basic oxygen furnace slag	Separates BOF slag into three products allowing greater iron recovery and recycling and uses low-grade iron byproduct for acid mine neutralization.	BOF Steelmaking	Estimated savings of 0.12 MMBtu/ton (0.14 GJ/tonne)	229 Btu/lb	No	Value is higher than SOA energy intensity	DOE 2002, IMP 2006, Energetics 2005
EPC System for Side Charging and Scrap Preheating	Design to allow continuous charging of preheated scarp into the EAF, including separation of preheating and cold scrap charging. Reduces gas flows, uses a totally sealed system and provides substantial reduction in dust and other emissions.	EAF Steelmaking	Preheating of scrap up to 700 °C reduces EAF energy consumption by up to 100 kWh/tonne of molten steel.	930 Btu/lb	No	Contiarc furnace provides a lower baseline energy use.	KR Tec n.d., Rummler et al. n.d.
Contiac Furnace	Replaces the ladle metallurgy furnace with a continuous series of vessels,	EAF Steelmaking	Reduced energy losses (200 kWh/ton) over conventional furnace	636 Btu/lb	No	PM energy intensity only just above TM energy intensity	AEHOF 2013, EPA 2012, IPPC 2013
Continuous casting for EAF		Casting	Anticipated 10% decrease in energy consumption	85 Btu/lb	No	Value is higher than SOA energy intensity	Peaslee et al. 2006, DOE 2005
Tundish heating technologies (cold tundish)	Using a cold tundish (heating a tundish inductively and not by combustion)	Casting	78% decrease in natural gas usage	85 Btu/lb	No	Value is higher than SOA energy intensity	Beraldo et al. 2003, EPA 2012, LBNL 2010b
Endless rolling	New development in thin slab casting and direct rolling	Rolling	Anticipated 40% lower energy than a traditional rolling mill	897 Btu/lb (hot rolling) 1,044 Btu/lb (cold rolling)	No	Value is higher than SOA energy intensity	Arvedi et al. 2008, EPA 2012

DRAFT

Technology Name	Description	Applicability	Explanation of energy savings assumptions	PM Energy Intensity (Btu/lb) or Percent savings (over baseline energy)	Included in PM model?	Reason for excluding (if applicable)	Reference
Next-generation system for scale-free steel reheating	Use of preheated or oxygen-enriched air to control flue gas. Improves the quality and yield of steel while increasing energy and production efficiency.	Rolling	Consumes 22-32% of current energy used for reheating; 0.2 GJ/tonne during reheating	1,410 Btu/lb (hot rolling) 1,655 Btu/lb (cold rolling)	No	Endless rolling provides a lower baseline energy use;	Thekdi 2010, DOE 2010
High temperature insulation materials	Innovative insulating materials that will limit their consumption in a furnace.	Rolling	Energy savings of 30-35% are possible; likely savings of 2-5% on furnaces	1,425 Btu/lb (hot rolling) 1,670 Btu/lb (cold rolling)	No	Endless rolling provides a lower baseline energy use.	BMWi 2008, EPA 2012
New High-Temperature, Low-Cost Ceramic Media for Natural Gas Combustion Burners	Combining four different technologies into a single radiant burner package that functions as both a burner and a catalyst support.	Crosscutting	Potential to reduce energy consumption by 25% for process heat.	16%	Yes		DOE 2011
Advanced Energy and Water Recovery Technology from Low-Grade Waste Heat	Recovery of high purity water and energy from low grade heat, high moisture waste streams using nanoporous membranes. Will prove concept in laboratory and evaluate in "two different types of industrial environments.	Crosscutting	The amount of energy savings would depend on the amount of waste heat could be recovered. Using the nanoporous membrane technology could increase heat recovery by 20-30% it would appear.	1%	Yes		DOE 2011c; GTI 2011
Control systems for energy-efficient recycling of steel residues	By utilizing computer-aided control of the process conditions, changes can be made in the prevailing conditions to reduce recycling energy consumption. In practical trials this software helped reduce energy consumption by 10%. The modular design of this software also enables changes to the processing conditions to reflect the desired product quality.	Crosscutting	Opportunity reduced to 2%.	2%	Yes		BMWi 2008

DRAFT

Table A5. Example Steel and AHSS R&D Technologies Considered for PM Energy Intensity Analysis

Subarea	Technology Name
Cokemaking	Single-chamber-system coking reactors
Cokemaking	Coal Moisture Control
Traditional Ironmaking	Top Pressure Recovery Turbines
Traditional Ironmaking	Drum Chute and Segregation Slit Charging
Traditional Ironmaking	Heat recovery from blast furnace slag
Steelmaking (BOF)	Recycling and reuse of basic oxygen furnace slag
Steelmaking (EAF)	EPC System for Side Charging and Scrap Preheating
Steelmaking (EAF)	Contiarc Furnace
Steelmaking (EAF)	Waste Heat Recovery for EAF
Casting	Continuous casting for EAF
Casting	Tundish heating technologies (cold tundish)
Rolling	Endless rolling
Rolling	Next-generation system for scale-free steel reheating
Rolling	High temperature insulation materials
Cokemaking	Production of Carbonite product to replace metallurgical coke for foundries and blast furnace
Steelmaking (BOF)	Aluminum-Bronze Alloy to Improve Hood Roof and Sidewall Life
Steelmaking (EAF)	ECOARC
Steelmaking (EAF)	Continuous Horizontal Sidewall Scrapping
Steelmaking (EAF)	Optical EAF Sensors
Steelmaking (EAF)	Nitrogen control in EAF by DRI fines injection
Steelmaking (EAF)	Electric arc furnace off-gas heat recovery
Steelmaking (EAF)	Rotary regenerators
Alternative Ironmaking/ Steelmaking	Plasma blast furnace
Alternative Ironmaking/ Steelmaking	IronArc plasma technology
Alternative Ironmaking/ Steelmaking	Molten Oxide Electrolysis
Alternative Ironmaking/ Steelmaking	Suspension hydrogen reduction of iron oxide concentrate
Alternative Ironmaking/ Steelmaking	FASTMET/FASTMELT
Alternative Ironmaking/ Steelmaking	Paired straight hearth furnace
Alternative Ironmaking/ Steelmaking	Tecnored process
Alternative Ironmaking/	Microwave Electric Arc Furnaces

DRAFT

Table A5. Example Steel and AHSS R&D Technologies Considered for PM Energy Intensity Analysis

Subarea	Technology Name
Steelmaking	
Alternative Ironmaking/ Steelmaking	Cyclone converter Furnace
Alternative Ironmaking/ Steelmaking	Coal and natural gas based HYL process for DRI
Alternative Ironmaking/ Steelmaking	FINEX Process
Casting	Near-net-shape casting [thin slab or strip casting]
Rolling	Thermochemical recuperation for steel reheating

DRAFT

DRAFT

U.S. DEPARTMENT OF
ENERGY
Energy Efficiency &
Renewable Energy

For more information, visit: manufacturing.energy.gov

DOE/EE-1346 • March 2016